

LAPIS GOLD SANDtm

Typical Physical Properties



info@kleenindustrialservices.com

800.356.7323

TYPICAL PHYSICAL PROPERTIES

	4x16 (4x16)	#8 (8x16)	#3 (8x20)	2/12 (12x20)
Color	Beige	Beige	Beige	Beige
Grain Shape	Sub-Angular	Sub-Angular	Sub-Angular	Sub-Angular
Roundness	0.8	0.75	0.7	0.7
Sphericity	0.6	0.75	0.7	0.8
Effective Size (mm)	1.3	1.19	1.09	1.03
Uniformity Coefficient	2.04	1.57	1.43	1.34
Specific Gravity (Apparent Density)	2.65	2.66	2.63	2.64
Moh's Hardness	6.9	6.6	6.9	6.9

TYPICAL PHYSICAL PROPERTIES

	2/16 (16x30)	1/20 (20x50)	0/30 (30x50)	#60 (40x70)
Color	Tan	Tan	Tan	Tan
Grain Shape	Sub-Angular	Sub-Angular	Sub-Angular	Sub-Angular
Roundness	0.7	0.6	0.6	0.6
Sphericity	0.7	0.7	0.8	0.8
Effective Size (mm)	0.73	0.52	0.37	0.22
Uniformity Coefficient	1.3	1.28	1.33	1.67
Specific Gravity (Apparent Density)	2.63	2.64	2.64	2.65
Moh's Hardness	6.9	7	7	6.9

